

ممتاز 10mm + 2.28PVB + 10mm واضحة بلوري الزجاج المقوى مغلقة لمصنعي الجدار الستار الخارجي.



ما هو 10mm + 2.28PVB + 10mm واضحة
متجمد الزجاج المغلفة تشديد؟

10mm+2.28PVB+10mm clear frosted toughened laminated glass is using a 10mm frosted toughened glass and one panel of 10mm clear toughened glass laminated by a “PVB” interlayer. The frosted glass is undergoing either an acid-etching process or sandblasting process to get a frosted obscure effect. For the difference between the acid-etching and sandblasting processes, you can check [this article](#).

The lamination undergoing a high temperature and high pressure in an autoclave finally result in permanent combinations of the glass and PVB material. Of course, if you need to ensure higher strength and better safety, you can adopt an [SGP interlayer](#). But if you need to have mesh or wire to be laminated inside the laminated glass, you could use [EVA interlayer](#), normally this will be adopted in interior designs .products



المنتجات التي يمكن استخدامها في الداخل.

مميزات:

1. **وظيفة السلامة:** بلوري الزجاج المغلفة هو زجاج السلامة متجمد. عندما تلف الألواح الزجاجية ، لن تنتشر القطع المكسورة ، وستبقى في لوحة كاملة تمنع الاختراق .
2. **وظيفة عازل للصوت:** يمكن أن تمنع الطبقة الفاصلة PVB انتقال الصوت. ولذلك يمكن للزجاج المغلفة تشديد وقف الضوضاء بشكل

- فعال من خلال الحصول على. خصوصا الضوضاء منخفضة التردد؛
3. **أضواء مضادة للأشعة فوق البنفسجية:** PVB تشديد الزجاج مغلفة يمكن أن توقف ما يقرب من 100٪ ضوء الأشعة فوق البنفسجية القادمة من خلال. ولذلك فإنه يمكن حماية الأثاث قيمة، والستائر، ويعرض من الألوان يتلاشى.
4. **وظيفة الديكور:** PVB يمكن أن يكون أي ألوان. يمكنك استخدام الأحمر والأزرق والأخضر والأرجواني والوردي، الخ لون للزينة، أو الجمع مع الطلاء، والسيراميك فريت عملية الطباعة لتعزيز الديكور لها.
5. **مميزات الأمان:** الأدوات العادية مثل المطارق، والعصي الحديد لا يمكن كسر الزجاج المغلفة تشديد. ولذلك لديها وظيفة لمكافحة السرقة.

المواصفات:

- اسم الإنتاج: 10mm + 2.28PVB + 10mm واضحة بلوري الزجاج المقوى مغلفة؛
- سمك الزجاج: 3 ~ 19mm؛
- الحد الأقصى للحجم: 3200 * 12000mm؛
- سمك PVB: مضاعف 0.38mm؛
- PVB الألوان: واضحة، متجمد، أحمر، أزرق، أخضر، وردي، ذهبي، الخ؛
- خيارات أخرى من الطبقة الفاصلة: SGP، إيفا؛
- التطبيقات: الأبواب والنوافذ والواجهات والمناور والأعمدة والصور والأرضيات والدرج، إلخ؛
- وقت الإنتاج: 7 ~ 15 يوما؛
- التعبئة: صناديق الخشب الرقائقي قوية؛
- العينات: عينة مجانية متاحة في 5 أيام؛
- الجودة: تخضع ل CE/ CCC/SGCC/AS/ISO9001، الخ.

نوعيه:

- زجاج مغلف متجمد يخضع ل CCC؛
- زجاج مغلف متجمد يخضع لSGCC؛
- زجاج مغلفة بلوري تخضع ل AS/NZS2208؛

الخ.

وظائف عازل للصوت:

الزجاج المغلفة تشديد لديه وظيفة عازل للصوت سوبر جيدة لأن PVB يمكن وقف انتقال الضوضاء. إذا كنت بحاجة إلى مرحاض هادئ أو غرفة مكتبية ، فإن الزجاج المغلف المقوى PVB سيكون خيارا جيدا!

 Soundproofing Performance Data		Noise frequency(HZ)																		STC
Glass structure	Glass configuration	100	125	160	200	250	315	400	500	630	800	1000	1250	1600	2000	2500	3150	4000	5000	
Monolithic	6	23	25	25	24	28	26	29	31	33	34	34	35	34	30	27	32	37	31	31
Laminated glass	6.38	27	23	27	24	27	28	29	31	33	35	35	35	33	31	32	37	41	45	33
	12.76	25	29	28	30	33	33	34	36	37	37	37	36	37	41	45	48	51	53	38
	13.52	26	29	28	30	33	33	35	36	37	38	38	37	38	41	44	47	51	54	39

الزجاج المغلف المقوى PVB هو الخيار الأفضل للصوت.

التطبيقات:

10mm + 2.28PVB + 10mm واضحة بلوري الزجاج المقوى مغلفة يمكن استخدامها كواجهة ، والجدران الزجاجية ، والمناور ، والفواصل ، الخ.



معلومات عامة عن الشركة

تفاصيل الإنتاج:



معلومات عامة عن الشركة

الشهادات:



. □ □ □ □ □ □ □ □

التعبئة التفصيل:



. 深圳龙玻璃有限公司 专业生产 钢化玻璃 夹层玻璃 中空玻璃

[Shenzhen Dragon Glass](#) is one of the best frosted laminated glass manufacturers in China. We have high automatic and advanced machines and production plants. We adopt the top quality float glass material and the best PVB interlayer together with the complete vacuum and high-pressure technologies, which can ensure providing excellent quality and complicated structural laminated glass for the clients. We exported our toughened laminated glass to clients around the world. Welcome to [contact us](#) now for your new projects